

Extrusion Processing Guidelines

PPC1GF1- (Any Color)

Extruder Barrel Temperatures

- Barrel Zone 1 370-390 °F
- Barrel Zone 2 370-400 °F
- Barrel Zone 3 380-410 °F
- Barrel Zone 4 380-410 °F

Material Drying is typically not required but for applications drying may be required. If needed dry at 160 – 190°F for 1-2 hours.

Die Temperatures

Zone 1	380-420°F
Zone 2	380-420°F
Screen Mesh	20-80
Screw Speeds	20-90 RPM
Sizers	When Applicable

Roll Temperatures

Top	220-260°F
Middle	190-230°F
Bottom	130-160°F

If you have any questions or require further processing information, please e-mail the Technical Service Group @ TechService@washpenn.com