

## Processing Guidelines

### TPE-PP-30A- (Any Color)

#### Pressures

|           |                |
|-----------|----------------|
| Injection | 600 - 1400 psi |
| Holding   | 150 - 700 psi  |
| Back      | 075 - 200 psi  |

#### Injection Speed

1.5 - 3.5 in/s

#### Temperatures

|                             |            |
|-----------------------------|------------|
| • Barrel Zone 1             | 350-380 °F |
| • Barrel Zone 2             | 350-380 °F |
| • Barrel Zone 3             | 360-390 °F |
| • Barrel Zone 4             | 360-390 °F |
| • Nozzle                    | 370-400 °F |
| • Hot Runner                | 370-400 °F |
| • Mold                      | 60-130 °F  |
| • Hydraulic Oil Temperature | 110-125 °F |

*Material Drying is typically not required but for some thin walled parts drying may be required. If needed dry at 160 – 190°F for 1-2 hours.*

#### Machine/Shot Information

|   |                |
|---|----------------|
| Shot Capacity vs. Barrel Capacity   | 2.5 to 4.0     |
| Cushion   | 1/8" to 1/4"   |
| Screw Decompression   | 0.10" to 0.25" |
| Clamp Tonnage should be 2.5 to 4.0 Tons per square inch of projected part area. |                |

If you have any questions or require further processing information, please e-mail the Technical Service Group @ [TechService@washpenn.com](mailto:TechService@washpenn.com)