

## Processing Guidelines

### TPO 3930- (Any Color)

#### Pressures

Injection	41 - 097 Bar
Holding	10 - 062 Bar
Back	05 - 10 Bar

#### Injection Speed

1.9 - 6.3 cm/s

#### Temperatures

• Barrel Zone 1	193-215 °C
• Barrel Zone 2	193-215 °C
• Barrel Zone 3	198-221 °C
• Barrel Zone 4	198-221 °C
• Nozzle	204-226 °C
• Hot Runner	204-226 °C
• Mold	15-60 °C
• Hydraulic Oil Temperature	43-52 °C

*Material Drying is typically not required but for some thin walled parts drying may be required.  
If needed dry at 71 – 87°C for 1-2 hours.*

#### Machine/Shot Information

Shot Capacity vs. Barrel Capacity	2.5 to 4.0
Cushion	0.32 to 0.65 cm
Screw Decompression	0.25 to 0.64 cm
Clamp Tonnage should be	1.0 to 1.6 Tons per square cm of projected part area.

If you have any questions or require further processing information, please e-mail the Technical Service Group @ [TechService@washpenn.com](mailto:TechService@washpenn.com)