

## Processing Guidelines

### PPC2CF3- (Any Color)

#### Pressures

|           |                |
|-----------|----------------|
| Injection | 600 - 1400 psi |
| Holding   | 150 - 900 psi  |
| Back      | 075 - 150 psi  |

#### Injection Speed

0.75 - 2.5 in/s

#### Temperatures

- Barrel Zone 1 430-450 °F
- Barrel Zone 2 430-450 °F
- Barrel Zone 3 430-460 °F
- Barrel Zone 4 430-460 °F
- Nozzle 430-470 °F
- Hot Runner 430-470 °F
- Mold 60-140 °F
- Hydraulic Oil Temperature 110-125 °F

*Material Drying is typically not required but for some thin walled parts drying may be required. If needed dry at 160 – 190°F for 1-2 hours.*

#### Machine/Shot Information

|   |                |
|---|----------------|
| Shot Capacity vs. Barrel Capacity   | 2.5 to 4.0     |
| Cushion   | 1/8" to 1/4"   |
| Screw Decompression   | 0.10" to 0.25" |
| Clamp Tonnage should be 2.5 to 4.0 Tons per square inch of projected part area. |                |

If you have any questions or require further processing information, please e-mail the Technical Service Group @ [TechService@washpenn.com](mailto:TechService@washpenn.com)